

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : G02B 5/128	A1	(11) International Publication Number: WO 98/22837 (43) International Publication Date: 28 May 1998 (28.05.98)
(21) International Application Number: PCT/US97/21082 (22) International Filing Date: 18 November 1997 (18.11.97) (30) Priority Data: 8/307821 19 November 1996 (19 (71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US). (72) Inventor: MORI, Yubaka; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). (74) Agents: CLEVELAND, David, R. et al.; Minnesota Mining and Manufacturing Company, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).	(81) Designated States: CA, CN, KR, MX, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published International search report. expiration of the time limit for amending the claims, the International search report will be republished in the event of the receipt of	
(54) Title: RECTROREFLECTIVE SHEET <div data-bbox="352 1178 1239 1541"> </div> (57) Abstract <p>To provide a retroreflective sheet which is suitable for co-molding by injection molding or the like, wherein the retroreflective sheet can be laid within a mold and molded with a resin to form a molded product, and, after molding, the sheet retains a significant portion of its reflection luminance and appearance as compared with the reflection luminance value before molding. A retroreflective sheet used for a co-molding, comprising a metallic reflective layer, a microspherical lens layer disposed as a single layer, and a transparent focal resin layer disposed between the reflective layer and the microspherical lens layer, in which the focal resin layer comprises a mixture of cellulose ester and polyvinyl butyral resin.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KR	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

WO 98/22837

PCT/US97/21082

RETROREFLECTIVE SHEET

TECHNICAL FIELD

The present invention relates to a retroreflective sheet for use on traffic signs, which enables safe utilization of roads at night, or labels, stickers, emblems or the like for vehicles or decorative purposes. More particularly, the present invention relates to a sealed lens type retroreflective sheet which is suitable for co-molding by injection molding, blow molding or the like wherein a retroreflective sheet can be placed within a mold for a curved substrate and molded with a resin to form a molded product having a curved surface, and, after molding, the sheet retains a significant portion of its reflection luminance as compared with the reflection luminance value before molding. That is, the present invention relates to a sealed lens type retroreflective sheet which, at the time of molding, enables a resin with the retroreflective sheet mounted thereon to be stretched to a desired form without undesirable deterioration in its optical properties.

BACKGROUND

In conventional sealed lens type retroreflective sheet, a transparent microspherical lens is independently embedded in a transparent anchoring layer, and a metallic reflective layer is provided on the back side of the microspherical lens through a focal resin layer. In these sealed lens type retroreflective sheet, since a microspherical lens is embedded in a thin sheet material, problems occur such as embrittlement and blister. Further, such a retroreflective sheet is unsuitable for co-molding wherein the retroreflective sheet is molded together with a substrate on which the retroreflective sheet is to be laminated. For this reason, Japanese Unexamined Patent Publication (Kokai) No. 63-27884 discloses that a single backing film layer is provided to reinforce the sheet, thereby solving the embrittlement problem. On the other hand, in Japanese Unexamined Patent Publication (Kokai) No. 59-5051, stretching is carried out so as to cause cracking in a metallic reflective layer to prepare an intermediate product having discontinuous

WO 98/22837

PCT/US97/21082

portions, and, thereafter, the other layers are formed. That is, the blister problem is solved by improving the air permeability.

Mounting of a sealed lens type retroreflective sheet on a flat substrate has hitherto been performed by contact-bonding the sheet to the substrate by taking
5 advantage of a pressure-sensitive adhesive provided on the surface of the sheet remote from the reflecting surface. Further, in the case of mounting of a retroreflective sheet on an uneven surface like a gentle quadratic surface, contact bonding has been used as with the case of the flat substrate. In these cases, the retroreflectivity of the retroreflective sheet can be maintained after mounting
10 because the retroreflective sheet per se is not substantially stretched by the mounting operation. This method, however, is unsuitable for mounting on a quadratic surface having sharp irregularities because the sheet cannot be exactly fitted to such a surface without leaving any space. For this reason, a co-molding method is used wherein the retroreflective sheet is mounted when the resin is
15 molded by injection molding or blow molding. In this case, the retroreflective sheet is stretched. The stretching of the sheet results in stretching of the focal resin layer. This means that the resin constituting the focal resin layer, for example, polyvinyl butyral, is also stretched. The stretching of the focal resin layer causes the thickness of the resin layer to gradually decrease with an increase in percentage stretching,
20 making the luminance of the sheet decrease. Further stretching thereof causes large cracks in the focal resin layer, making it impossible to maintain the appearance as before the molding.

SUMMARY OF THE INVENTION

25 The present invention provides, in one aspect, a sealed lens type retroreflective sheet having good appearance, which is suitable for co-molding by injection molding, blow molding or the like wherein the retroreflective sheet can be laid within a mold for a substrate, the sheet and a molding resin can be combined to form a molded product, and, after molding, the sheet retains a significant portion of
30 its reflection luminance as compared with the reflection luminance value before molding.

WO 98/22837

PCT/US97/21082

A preferred sealed lens retroreflective sheet of the invention can be used for co-molding, and comprises a metallic reflective layer, a microspherical lens layer disposed as a single layer, and a transparent focal resin layer disposed between the reflective layer and the microspherical lens layer, characterized in that the focal resin layer comprises a mixture of cellulose ester and polyvinyl butyral resin. Preferably, the focal resin layer consists essentially of a cellulose ester and a polyvinyl butyral resin.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a cross-sectional view of a representative structure of a conventional retroreflective sheet and a representative structure of a retroreflective sheet of the present invention.

Fig. 2 is a graph showing incidence angles vs. reflection luminances (R') at an observation angle of 0.2° of a conventional retroreflective sheet.

Fig. 3 is a graph showing incidence angles vs. reflection luminances (R') at an observation angle of 0.33° of a conventional retroreflective sheet.

Fig. 4 is a graph showing incidence angles vs. reflection luminances (R') at an observation angle of 2° of a conventional retroreflective sheet.

Fig. 5 is a graph showing incidence angles vs. reflection luminances (R') at an observation angle of 0.2° of a retroreflective sheet of the present invention.

Fig. 6 is a graph showing incidence angles vs. reflection luminances (R') at an observation angle of 0.33° of a retroreflective sheet of the present invention.

Fig. 7 is a graph showing incidence angles vs. reflection luminances (R') at an observation angle of 2° of a retroreflective sheet of the present invention.

Fig. 8 is a graph showing incidence angles vs. reflection luminances (R') at an incidence angle of 5° .

Fig. 9 is a graph showing incidence angles vs. reflection luminances (R') at an incidence angle of 30° .

Fig. 10 is a graph showing incidence angles vs. reflection luminances (R') at an incidence angle of 40° .

WO 98/22837

PCT/US97/21082

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

Specifically, the retroreflective sheet according to the present invention is suitable for co-molding wherein the sheet can be laid within a mold for a substrate and molded with a resin to form a molded product. In this case, when the whole sheet is stretched to form the molded product, the focal resin layer is not stretched to the same extent as the sheet because the focal resin layer has an elongation at break which is less than the elongation at break for the whole sheet. The thickness of the focal resin layer also remains substantially unchanged, and it is uniformly and finely cracked by individual microspherical lens particles or groups of particles. Further, the metallic reflective layer exhibits substantially the same behavior as the focal resin layer and causes uniform and fine cracking. Due to the uniform and fine cracks, the appearance of the retroreflective sheet does not deteriorate. Further, the relative positions of the spherical lens and the metallic reflective layer remain substantially unchanged for each particle or particle group formed by cracking, thus enabling the focal point to remain substantially unchanged in many portions. Therefore, there is a reduced decrease in reflection luminance due to molding.

As shown in Fig. 1, a typical embodiment of the retroreflective sheet according to the present invention comprises a laminate of a clear layer 1, a support layer 2, an anchoring agent layer 3, a layer 4 of a microspherical lens, a focal resin layer 5, a metallic reflective layer 6, an adhesive layer (1) 7, and an adhesive layer (2) 8. However, the retroreflective sheet according to the present invention is not limited to the retroreflective sheet having the above construction. Materials for constituting the retroreflective sheet according to the present invention may be the same as those constituting the conventional product except for the focal resin layer, so far as the following requirements are met.

The clear layer 1 may be formed of any resin having good moldability, good weather resistance, and excellent transparency, preferably urethane resin, fluororesin or the like. The thickness of the clear layer is preferably 20 μm to 150 μm . When it is less than 20 μm , the weather resistance is deteriorated, while when it exceeds 150 μm , the moldability is deteriorated.

WO 98/22837

PCT/US97/21082

The support layer 2 is formed of preferably a resin having good moldability, excellent transparency, and excellent adhesion to the clear layer 1 and the anchoring agent layer 3, such as PVC resin or urethane resin. The thickness of the support layer is preferably not more than about 150 μm . When it exceeds 150 μm , the transparency and the moldability are deteriorated. When the total thickness of the clear layer 1 and the adhesive layer (2) exceeds 100 μm , sufficient strength for withstanding molding is ensured enabling the support layer to be omitted.

The anchoring agent layer 3 is formed of preferably a resin having good moldability, excellent transparency, and excellent adhesion to the support layer 2 and the microspherical lens 4, such as a urethane resin. The thickness of the anchoring agent layer is preferably such that the microspherical lens is embedded therein by half. When it is excessively small, the adhesion of the microspherical lens is deteriorated, while when it is excessively large, the retroreflectivity is lost.

The microspherical lens 4 is formed of preferably a glass having a refractive index of 2.2 to 2.3. When the refractive index is less than 2.2, it becomes difficult to reproduce the retroreflectivity. A material having a refractive index exceeding 2.3 is difficult to prepare on a commercial scale. The microspheres preferably have an average diameter of about 30 μm to about 100 μm , more preferably about 50 μm to about 80 μm .

The metallic reflective layer 6 is preferably formed by vapor deposition of a metal. The vapor deposition product of a metal having good adhesion to the focal resin layer 5 and the adhesive layer (1) 7 and high reflectivity, such as aluminum or tin, is preferred. The thickness of the reflective layer 6 is preferably 300 angstrom (\AA) to 800 \AA . When it is less than 300 \AA , the amount of light passed through this layer becomes large, that is, the reflectivity is deteriorated. On the other hand, when the thickness exceeds 800 \AA , the reflectivity may become saturated.

The adhesive layer (1) 7 preferably is employed when the reflective layer 6 has poor adhesion to the adhesive layer (2) 8. Since the adhesive layer (2) 8 is typically formed of an olefin or an ABS resin which often is the same material as the substrate which will be adhered to the adhesive layer (2) 8, the adhesive layer (1) 7 is preferably formed of a urethane adhesive. The thickness of this layer is preferably

WO 98/22837

PCT/US97/21082

such that the microspherical lens is embedded therein at least by half. When it is smaller than this, the adhesion to the microspherical lens is deteriorated. The upper limit of the thickness of the adhesive layer (1) 7 is preferably a value of (a thickness sufficient to embed the microspherical lens by half + 50 μm). When the thickness
5 exceeds this value, the moldability may be deteriorated.

As described above, the adhesive layer (2) 8 is formed of an olefin resin or an ABS resin which is the same material as the substrate. The thickness of the adhesive layer (2) 8 is preferably 20 μm to 150 μm . When it is less than 20 μm , the productivity may be lowered, while when it exceeds 150 μm , the moldability may be
10 lowered.

The focal resin layer 5 preferably has excellent transparency, and the elongation at break of the focal resin layer 5 per se preferably is 0 to about 25%. Preferably, this resin layer is formed of a mixture substantially of a polyvinyl butyral resin, having a good adhesion to the microspherical lens layer and the metallic
15 reflective layer, with a brittle cellulose ester. Preferably, the cellulose ester is a cellulose acetate propionate or a cellulose acetate (hereinafter referred to as "cellulose acetate propionate or the like"). If the content of cellulose ester, such as cellulose acetate propionate or the like, is excessively high, then it is difficult to form uniform cracks in the microspherical lens layer and the metallic reflective layer,
20 and the appearance of the sheet may deteriorate. That is, if the elongation at break of the focal resin layer is 10% or less, then the focal resin layer alone tends to form uniform cracks (see Table 4). However, if the ratio of polyvinyl butyral resin relative to cellulose ester such as cellulose acetate propionate or the like is too low, the adhesion of the microspherical lens layer to the focal resin layer may become
25 poor. Accordingly, the weight ratio of polyvinyl butyral resin relative to cellulose ester is preferably sufficiently high to provide an adhesively effective amount of polyvinyl butyral resin, and more preferably is at least about 3:7 by weight, and most preferably is in a range from about 4:6 to about 6:4. The cellulose ester is selected as one component of the resin mixture for composing the focal resin layer
30 because the deformation is less during the molding process (at a high temperature) due to its high glass transition point. Also, it is hard and brittle, and a solution

WO 98/22837

PCT/US97/21082

thereof in an organic solvent, which is a poor solvent, has a high viscosity and a low solid content.

The polyvinyl butyral resin is selected as another component of the focal resin layer because it has a good compatibility with the cellulose ester and a good
5 adhesion to the microspherical lens layer. Also a solution thereof in an organic solvent which is a poor solvent has a high viscosity and a low solid content.

Examples of suitable commercially available cellulose ester resins and polyvinyl butyral resins includes cellulose ester available from Eastman Chemical Japan Ltd., Tokyo, Japan, and Butver B-76 available from Monsanto Company, St.
10 Louis, MO, respectively.

Preferably, the reflective sheet can generate the retroreflection in response to incident rays of various incident angles. To have such a function, the focal resin layer 5 should have a uniform thickness along the microspherical lenses 4, which state is attainable when the solid content of the focal resin solution is relatively low
15 (about 20% by weight) and the viscosity thereof is high. Such an ideal state is obtained when this resin is dissolved in a poor solvent to cellulose acetate propionate, such as diacetone alcohol. To form the focal resin layer from this solution, the solution is poured onto the microspherical lenses half embedded into the anchoring layer, and thereafter the solvent thereof is evaporated. The preferable
20 thickness of the focal resin layer changes when the diameter of microspherical lens changes, even if the refractive index of the microspherical lens is constant, and it also changes when the refractive index of the lens changes. A thickness of the focal resin layer is preferably in a range from 20 μm to 28 μm , more preferably from 22 μm to 26 μm if the microspherical lens has a refractive index of 2.26 and a diameter
25 of 71 μm . If the thickness is outside this range, the retroreflectivity becomes poorer.

The retroreflective sheet of the present invention can be previously laid within a mold for a substrate and, simultaneously with molding of a resin, mounted on the resultant molded product. In this case, as compared with a retroreflective
30 sheet using a resin which, when molded, is likely to be stretched, the thickness of the resin layer remains unchanged, and, further, the position of the microspherical

WO 98/22837

PCT/US97/21082

lens layer relative to the metallic reflective layer remains unchanged, thus enabling the focal point to remain unchanged in many portions. Therefore, a reduction in luminance after molding is small.

5

EXAMPLES

Advantages of the invention are illustrated by the following examples.

However, the particular materials and amounts thereof recited in these examples, as well as other conditions and details, are to be interpreted to apply broadly in the art and should not be construed to unduly limit the invention.

10

Example 1 and Comparative Example 1

The following samples were prepared in order to examine a change in reflection luminance after molding for the sealed lens type reflective sheet of the present invention and the conventional sealed lens type reflective sheet. A support layer, an anchoring layer, a glass bead layer, a focal resin layer and a reflective layer were formed in accordance with the procedure, described in Japanese Unexamined Patent Publication (Kokai) No. 59-5051 on page 3, left top column, line 6, from bottom to right top column, line 6. In the present example and comparative example, the diameter of glass bead (microspherical lens) used was 71 μm . A solution (solid content 30%) of MACROMELT 6240 as an adhesive, manufactured by Henkel Hokusui Corp., Kankakee, IL, in isopropanol:toluene = 1:1 solvent, was coated by means of a bar coater on the reflective layer, and the coating was then dried to form a layer, having an average thickness of 20 μm , as an adhesive layer (1) 7. A 50 μm -thick polypropylene, subjected to corona discharge treatment, was heat-laminated as an adhesive layer (2) 8 at 90°C to the adhesive layer (1) 7. The release paper provided on the surface of the support layer 2 remote from the adhesive layer (2) 8 was peeled off, NEOPAC R9000 manufactured by Zeneca Resins, Wilmington, MA., an acrylic urethane resin, was coated by means of a bar coater on the exposed surface of the support layer 2, and the coating was then dried to form a 50 μm -thick clear layer 1. As the focal resin layer, a polyvinyl butyral

WO 98/22837

PCT/US97/21082

resin was used. Thus, a conventional retroreflective sheet (Comparative Example 1) was prepared.

The procedure from the initial step to the step of coating glass beads described above in connection with the preparation of the conventional retroreflective sheet was repeated. Thereafter, a mixture of cellulose acetate propionate CAP-504-0.2 manufactured by Eastman Chemical and a polyvinyl butyral resin (solid content ratio = 50:50) was coated by means of a bar coater to an average thickness of 20 μm to form a focal resin layer 5. Aluminum was vapor-deposited thereon to a thickness of 600 \AA by using a vacuum evaporator EX-400 manufactured by Ulvac Technologies, Inc., Andover, MA, to form a reflective layer 6. A clear layer 1 and the adhesive layers (1) 7 and (2) 8 were prepared and laminated in the same manner as described above in connection with the preparation of the conventional retroreflective sheet, thereby preparing a retroreflective sheet of the present invention (Example 1).

Samples for the measurement of reflection luminance after molding were prepared from the two retroreflective sheets thus prepared. Samples having a size of 13 cm \times 25 cm from these retroreflective sheets were stretched by 1 time, 1.25 times, 1.5 times, and 1.75 times in the longitudinal direction at a rate of 100 mm/minute with a chuck width of 2.5 cm (distance between upper and lower chucks: 20 cm) by using a tensile tester UCT-100 manufactured by Orientec Company Ltd., Tokyo, Japan, and laminated onto an aluminum sheet coated with an adhesive. After the lamination, the percentage stretching in terms of the actually stretched area was measured, and the peripheral portion of the samples (that is, the whole area except for the central area 8 cm \times 15 cm) was masked with a pressure-sensitive paper tape to prepare samples for the measurement of reflection luminance. The reflection luminance was measured according to JIS Z9117-1984, provided that sample area 8 cm \times 15 cm was used instead of the sample area 21 cm \times 15 cm. Specifically, the coefficient of reflection luminance, R_l , was measured under conditions of angles of observation of 0.2°, 0.33°, and 2° and angles of incidence of 5° to 90° in an increment of 5° to compare the reflection

WO 98/22837**PCT/US97/21082**

luminance before stretching with that after stretching. The results are shown in Tables 1 and 2 and Figs. 2 to 10.

WO 98/22837

PCT/US97/21082

TABLE 1
REFLECTION LUMINANCE OF CONVENTIONAL RETROREFLECTIVE SHEET (COMPARATIVE EXAMPLE 1)

Angle of incidence	1 time: stretching 0%			1.25 times: stretching 15.4%			1.5 times: stretching 29.5%			1.75 times: stretching 41.2%		
	Angle of observation (°)			Angle of observation (°)			Angle of observation (°)			Angle of observation (°)		
	0.2	0.33	2	0.2	0.33	2	0.2	0.33	2	0.2	0.33	2
5	101	77.2	7.35	40.4	31.2	5.51	14.7	12.8	3.67	9.19	7.35	3.67
10	97.4	73.5	7.35	38.6	31.2	5.51	14.7	11	3.67	7.35	7.35	1.83
15	90	68	7.35	36.7	27.5	5.51	12.8	11	3.67	7.35	5.51	1.83
20	79	60.6	7.35	33	25.7	5.51	11	9.19	3.67	5.51	5.51	1.83
25	64.3	49.6	7.35	25.7	20.2	3.67	9.19	7.35	1.83	5.51	3.67	1.83
30	47.7	38.6	7.35	18.3	16.5	3.67	7.35	5.51	1.83	3.67	3.67	1.83
35	33	27.5	5.51	12.8	11	3.67	5.51	5.51	1.83	3.67	3.67	1.83
40	20.2	18.3	5.51	9.19	9.19	3.67	3.67	3.67	1.83	3.67	3.67	1.83
45	11	11	3.67	5.51	5.51	1.83	3.67	3.67	1.83	3.67	3.67	1.83
50	5.51	7.35	3.67	3.67	3.67	1.83	3.67	3.67	1.83	1.83	1.83	1.83
55	3.67	3.67	1.83	3.67	3.67	1.83	1.83	1.83	0	1.83	1.83	1.83
60	1.83	1.83	1.83	1.83	1.83	1.83	1.83	1.83	0	1.83	1.83	1.83
65	1.83	0	1.83	1.83	1.83	1.83	1.83	1.83	0	1.83	1.83	0
70	0	0	0	1.83	1.83	0	0	0	0	1.83	0	0
75	0	0	0	1.83	1.83	0	0	0	0	0	0	0
80	0	0	0	0	1.83	0	0	0	0	0	0	0
85	0	0	0	0	1.83	0	0	0	0	0	0	0
90	0	0	0	0	0	0	0	0	0	0	0	0

WO 98/22837

PCT/US97/21082

TABLE 2
REFLECTION LUMINANCE OF RETROREFLECTIVE SHEET OF THE PRESENT INVENTION (EXAMPLE 1)

Angle of incidence	1 time: stretching 0%			1.25 times: stretching 19.2%			1.5 times: stretching 35.0%			1.75 times: stretching 52.1%		
	Angle of observation (°)			Angle of observation (°)			Angle of observation (°)			Angle of observation (°)		
	0.2	0.33	2	0.2	0.33	2	0.2	0.33	2	0.2	0.33	2
5	90	58.8	9.19	42.2	29.4	5.51	25.7	20.2	3.67	22	16.5	3.67
10	88.2	58.8	9.19	40.4	29.4	5.51	25.7	18.3	3.67	20.2	16.5	3.67
15	84.5	58.8	9.19	38.6	27.5	5.51	23.8	18.3	3.67	20.2	14.7	3.67
20	79	56.9	9.19	36.7	27.5	5.51	22	16.6	3.67	18.3	14.7	3.67
25	69.8	51.4	7.35	33	25.7	5.51	18.3	14.7	3.67	16.5	12.8	3.67
30	58.8	45.9	7.35	27.5	22	5.51	16.5	12.8	3.67	14.7	17	3.67
35	47.7	38.6	7.35	23.8	18.3	5.51	12.8	11	3.67	12.8	9.19	3.67
40	36.7	29.4	7.35	18.3	14.7	3.67	11	9.19	1.83	9.19	7.35	1.83
45	25.7	22	7.35	12.8	11	3.67	7.35	7.35	1.83	7.35	5.51	1.83
50	18.3	16.5	5.51	9.19	7.35	3.67	5.51	5.51	1.83	5.51	5.51	1.83
55	11	11	3.67	5.51	5.51	1.83	3.67	3.67	1.83	3.67	3.67	1.83
60	7.35	7.35	3.67	3.67	3.67	1.83	1.83	1.83	1.83	1.83	1.83	1.83
65	3.67	3.67	1.83	3.67	1.83	1.83	1.83	1.83	0	1.83	1.83	0
70	1.83	1.83	1.83	1.83	1.83	1.83	1.83	1.83	0	1.83	1.83	0
75	1.83	1.83	0	1.83	1.83	0	1.83	1.83	0	1.83	1.83	0
80	0	0	0	1.83	0	0	0	0	0	1.83	0	0
85	0	0	0	1.83	0	0	0	0	0	0	0	0
90	0	0	0	0	0	0	0	0	0	0	0	0

WO 98/22837

PCT/US97/21082

From the above Tables 1 and 2 and Figs. 2 to 10, regarding the reduction in reflection luminance after molding as compared with the reflection luminance before molding, the retroreflective sheet of the present invention exhibits better retention of reflection luminance than the conventional retroreflective sheet. This is derived from the difference in the material constituting the focal resin layer between the retroreflective sheet of the present invention and the conventional retroreflective sheet.

Example 2

Tests were carried out for confirming whether or not the appearance of the retroreflective sheet remains unchanged due to the existence of cracking in the focal resin layer generated after the molding as compared with prior to the molding.

Samples were prepared in the same manner as Example 1, except that the average thickness of the focal resin layer is made to vary from 10 μm to 150 μm so that a size of fracture of the focal resin layer varies in the molding.

These samples were stretched by 1.25 times by using the same tensile tester as Example 1, and the appearance uniformly thereof was observed at a distance 1.0m in a 90°C direction from the sample, while using a standard light source manufactured by the Macbeth Division of Kollmorgen Instr. Corp., New Windsor, NY. The test results were evaluated by a three rank method; good, fair, bad.

TABLE 3

Focal resin layer Fracture size	Uniformity of appearance					
	Panel A	Panel B	Panel C	Panel D	Panel E	Total
< 0.5 mm	good	good	good	good	good	good
0.5 to 1.0 mm	good	good	good	good	good	good
1.0 to 2.0 mm	fair	good	fair	fair	bad	fair
> 2.0 mm	bad	bad	bad	bad	bad	bad

From the above Table 3, it was confirmed that, when the fracture size is 2.0 mm or less, the appearance of the retroreflective sheet according to the present invention remains nearly unchanged even after the molding, and if the fracture size

WO 98/22837

PCT/US97/21082

is 1 mm or less, a more favorable appearance is maintained, closer to that prior to molding.

Example 3

5 A tensile strength and an elongation at break of the focal resin layer alone; a tensile strength, an elongation at break and an evenness of crack generation (uniformity of appearance), and an adhesion between the focal resin layer and the glass beads of the retroreflective sheet were measured as follows:

10 (a) A film of 25 μ m thick was prepared by coating a solution of polybutyral resin and/or cellulose acetate propionate CAP-504-0.2 produced by Eastman Chemical in a 1:1 mixture of Ipzol #150 produced by Godo Solvent K.K., Tokyo, Japan, and cyclohexanone on a non-treated PET film, drying the coated film in an oven, and peeling the polyvinyl butyral film or others off from the PET film. The thus obtained film was cut into pieces of 2.5 cm \times 15 cm to be test samples.

15 (b) A retroreflective sheet was prepared in the same manner as Example 1, while using the resin in the test samples (a) as a focal resin layers to have the same thickness, which sheet was cut into pieces of 2.5 cm \times 15 cm to be test samples.

The above two kinds of test samples were subjected to a tensile test for
20 obtaining the elongation at break (in Table 4, merely referred to as "elongation") and the tensile strength while using a tensile tester UCT-100 provided by Orientec, with a grip width of 2.5 cm at a normal temperature and a stretching rate of 300 mm/min. Further, the evenness of crack generation (which is the same as uniformity of appearance in Example 2) and the adhesion between the focal resin
25 layer and the glass beads was visually evaluated on the test samples (b). If the focal resin had poor adhesion to the microspheres (denoted in Table 4 as "no good"), then the resin tended to peel away from the microspheres when the focal resin cracked during sample elongation.

30 These results were listed in Table 4. In Table 4, the polyvinyl butyral resin is merely referred to as "butyral"; the elongation at break as "elongation"; and the adhesion between the focal resin layer and the glass beads as "adhesion".

WO 98/22837

PCT/US97/21082

As apparent from Table 4, if the elongation is 10% or less, the focal resin layer alone generates uniform cracks in the retroreflective sheet, and if the ratio of the polyvinyl butyral resin relative to the sum of itself and the polyvinyl propionate by weight is 3/10 or less, the adhesion between the focal resin layer and the glass beads becomes poor.

TABLE 4

Butyral: Cap-504-0.2 weight %	<u>Focal resin layer alone</u>		<u>Retroreflective sheet</u>			
	Strength (kgf)	Elongation (%)	Strength (kgf)	Elongation (%)	Crack evenness	Adhesion
10:0	2.19	63.0	10.82	195.5	no good	good
9:1	1.91	43.3	10.26	189.0	no good	good
8:2	1.84	21.1	10.54	187.3	no good	good
7:3	1.91	33.6	10.05	172.6	no good	good
6:4	2.55	8.46	9.86	165.9	good	good
5:5	2.35	3.51	10.55	168.2	good	good
4:6	2.15	3.45	11.03	170.1	good	good
3:7	2.45	4.12	10.79	177.4	good	no good
2:8	2.42	3.27	10.28	165.2	good	no good
1:9	1.63	2.24	9.73	162.0	good	no good
0:10	1.88	2.58	9.95	154.6	good	no good

The complete disclosure of all patents, patent documents, and publications cited herein are incorporated by reference. The foregoing detailed description and examples have been given for clarity of understanding only. No unnecessary limitations are to be understood therefrom. The invention is not limited to the exact details shown and described, for variations apparent to one skilled in the art will be included within the invention defined by the claims.

WO 98/22837

PCT/US97/21082

CLAIMS:

1. A retroreflective sheet useful for co-molding, comprising a metallic reflective layer, a microspherical lens layer disposed as a single layer, and a
5 transparent focal resin layer disposed between the reflective layer and the microspherical lens layer, characterized in that the focal resin layer comprises a mixture of cellulose ester and polyvinyl butyral resin.
2. The retroreflective sheet of claim 1, further characterized in that the
10 cellulose ester comprises cellulose acetate.
3. The retroreflective sheet of claim 1, further characterized in that the cellulose ester comprises cellulose acetate propionate.
- 15 4. The retroreflective sheet of claim 1, further characterized in that the focal resin layer consists essentially of cellulose ester and polyvinyl butyral resin.
5. The retroreflective sheet of claim 4, further characterized in that the cellulose ester and the polyvinyl butyral resin are present in the focal resin layer in a
20 weight ratio of from 4:6 to 6:4.
6. The retroreflective sheet of claim 5, further characterized in that the microspherical lens layer comprises microspheres comprising glass having a refractive index of 2.2 to 2.3.
25
7. The retroreflective sheet of claim 6, further characterized in that the metallic reflective layer has a thickness of 300Å to 800Å.

WO 98/22837

PCT/US97/21082

8. The retroflective sheet of claim 1, further characterized in that the microspherical lens layer is embedded in an anchoring agent layer which is disposed on a support layer.


5

9. The retroflective sheet of claim 8, further characterized in that the metallic reflective layer has two adhesive layers disposed thereon.


WO 98/22837

PCT/US97/21082

1/5

Fig. 1**Fig. 2**



Entrance angle vs. R' on observation angle 0.2 degree



WO 98/22837

PCT/US97/21082



2/5

Fig. 3Entrance angle vs. R' on observation angle 0.33 degree**Fig. 4**Entrance angle vs. R' on observation angle 2 degree

WO 98/22837

PCT/US97/21082

3/5

Fig. 5Entrance angle vs. R' on observation angle 0.2 degree**Fig. 6**Entrance angle vs. R' on observation angle 0.33 degree


WO 98/22837

PCT/US97/21082


4/5

Fig. 7

Entrance angle vs. R' on observation angle 2 degree

**Fig. 8**

Drawing ratio vs. R' on entrance angle 5 degree




WO 98/22837

PCT/US97/21082


5/5

Fig. 9

Drawing ratio vs. R' on entrance angle 30 degree

**Fig. 10**

Drawing ratio vs. R' on entrance angle 40 degree



INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 97/21082

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 G02B5/128

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 256 721 A (WILSON BRUCE B ET AL) 26 October 1993 see column 4, line 31 - line 48 see column 7, line 40 - line 50 ---	1
A	EP 0 672 921 A (NIPPON CARBIDE KOGYO KK) 20 September 1995 see page 5, line 23 - line 29 ---	1
A	EP 0 699 519 A (SHELL INT RESEARCH) 6 March 1996 see page 2, line 3 - line 42 -----	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

16 March 1998

Date of mailing of the international search report

01.04.98

Name and mailing address of the ISA

European Patent Office, P.O. Box 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl
Fax: (+31-70) 340-3016

Authorized officer

Luck, W

Form PCT/ISA/210 (second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

Information on patent family members

Intern Application No

PCT/US 97/21082

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5256721 A	26-10-93	US 5008142 A	16-04-91
		AT 136124 T	15-04-96
		AU 619878 B	06-02-92
		AU 3923489 A	08-03-90
		DE 68926081 D	02-05-96
		DE 68926081 T	28-11-96
		EP 0360420 A	28-03-90
		IE 73485 B	04-06-97
		JP 2113078 A	25-04-90
		US 5262225 A	16-11-93
EP 0672921 A	20-09-95	JP 7261008 A	13-10-95
		CN 1115032 A	17-01-96
		US 5601915 A	11-02-97
EP 0699519 A	06-03-96	AU 3029795 A	14-03-96
		BR 9503819 A	16-04-96
		JP 8073700 A	19-03-96

Form PCT/ISA/210 (latest family member) / July 2002